

FUSED BAMBOO® LUMBER & PANELS



Use XTR lumber and panels to trim your projects correctly and build out coordinated site furnishings, privacy screens, fences, gates, railings and more.

Lumber offered in 20mm (¾") & 40mm (1½") thicknesses

dasso.XTR fused bamboo lumber is to be considered like unfinished lumber; it is S2S+RE2 (sides need to be planed). The material is not pre-primed so the user can finish it as they choose.

XTR-LUM20-205 1 x 8 nominal S4S Lumber
¾" x 8" x 73-¼" (20 x 205 x 1860mm)

XTR-LUM40-152 2 x 6 nominal S4S Lumber
1-½" x 6" x 73-¼" (40 x 152 x 1860mm)

Panels offered in 20mm (¾") & 40mm (1½") thicknesses

dasso.XTR fused bamboo panels are unfinished — not pre-primed. Panels come oversized to trim in two sizes: 1-½"x2'x6' and ¾"x2'x6'. Use dasso.XTR panels to creating outdoor furnishings for years of lasting beauty.

XTR-PAN20H 1" Half Panel
¾" x 24" x 73-¼" (20 x 623 x 1860mm)

XTR-PAN40H 2" Half Panel
1-½" x 24" x 73-¼" (40 x 623 x 1860mm)



dassoXTR
Fused Bamboo® for Exterior Use

Beautiful
Innovative
Dimensionally Stable
Performance Engineered



United States Patent No. US8,709,578 B2
European Union Patent No. 08800590.5
China Patent No. ZL200810093764.4

 CLASS A FIRE RATING



LUMBER & PANELS

dassoXTR
Fused Bamboo® for Exterior Use

DASSO GROUP
Xinhe Village, Linpu Town, Xiaoshan District,
Hangzhou, Zhejiang, China 311251
Tel.: +86 571 5716 3765
info@dassoGroup.com
dassoGroup.com

DASSO USA
6060 Boat Rock Blvd SW, Suite 800,
Atlanta, GA 30336 USA
P +1.404.691.6872
info@dassoXTR.com
dassoXTR.com


Fused Bamboo® offered in
DECKING | RAINCLAD® SIDING
PORCH FLOORING | LUMBER | PANELS

FUSED BAMBOO® DECKING



dasso's patented Fusion Process creates a dense, environmentally friendly, stable decking. Precision milled with tongue & grooved ends and reversible faces offering unique installation and performance advantages over traditional tropical hardwood decking.

Our 20mm / 3/4" Residential Decking is:



END MATCHED – Tongue & Grooved Ends
Allows installation on or off the joists



REVERSIBLE FACES – unlimited design possibilities
Install smooth or reeded face up




2 SIDE GROOVED – for main deck use with hidden fastening clips onto joists



1 SIDE GROOVED – for use as deck nosing / stairs / trim / fencing & more.

Our 40mm / 1-1/2" Commercial Decking offers all of the above but is not side grooved



XTR-DK20-G2-PP 1 x 6 Double Groove Decking
3/4" x 5-3/8" x 72" Pre-Primed
20 x 137 x 1829mm

XTR-DK20-G1-PP 1 x 6 Single Groove Decking
3/4" x 5-3/8" x 72" Pre-Primed
20 x 137 x 1829mm

XTR-DK40-G0-PP 2 x 6 Decking
1-1/2" x 5-3/8" x 72" Pre-Primed
40 x 137 x 1829mm




DECKING

FUSED BAMBOO® RAINCLAD® SIDING




The sustainable alternative to Tropical Hardwood siding. XTR is perfect for architectural designs requiring natural elements on exterior walls. Durable and stable, install with our RainClad® Clip Installation System on sheathing or battens.

1x6 RainClad® Siding with tongue & groove end-match



1x7 RainClad® Siding with tongue & groove end-match



XTR-SID18-137TG-PP 1 x 6 T&G RainClad® Siding
3/4" x 5-3/8" x 72" Pre-Primed
18 x 137 x 1829mm

XTR-SID18-178TG-PP 1 x 7 T&G RainClad® Siding
3/4" x 7" x 72" Pre-Primed
18 x 178 x 1829mm

ASD-RC3S-W Sheathing Fastener
for use with
RainClad Siding Plank



ASD-RFT-137G RainClad Fastrak
for 137MM (6") Siding

ASD-RFT-178G RainClad Fastrak
for 178MM (7") Siding




RAINCLAD® SIDING

FUSED BAMBOO® PORCH FLOORING



dasso.XTR Fused Bamboo® Porch Flooring welcomes visitors with an unmatched elegance unifying your outdoor spaces. dasso.XTR bamboo porch flooring has a tongue and groove fit, and outperforms common porch flooring in aesthetics and durability.

Porch Flooring



dasso.XTR Fused Bamboo® reversible tongue and groove Porch Flooring is ideal for covered walkways and porches to provide a more interior look.

XTR-POR18-96-PP 3/4" x 3-3/4" x 72"
18mm x 96mm x 1829mm

dasso.XTR FUSED BAMBOO COMPARISON

SKU	dassoXTR Classic	dassoXTR Epic	Ipe/ Brazilian Walnut	Meranti Batu	Western Red Cedar
Density lb/ft ³ (kg/m ³)	69 (1,100)	75 (1,200)	66 (1,060)	53 (850)	23 (370)
Strength MOR psi (MPa)	11,922 (82)	17,730 (122)	19,173 (132)	17,259 (119)	7,498 (52)
Stiffness MOE 1000 psi (MPa)	2,101 (14,490)	2,013 (13,880)	3,200 (22,070)	245 (16,950)	1,100 (7,584)
Janka Hardness Newton (lbf)	16,992 (3,820)	17,659 (3,970)	15,620 (3,510)	7,117 (1,600)	3,110 (700)
Shrinkage longitude %	0.02	0.06	0.16	0.17	0.20
width %	0.40	1.20	5.90	5.50	2.40
thickness %	1.90	3.70	7.20	10.10	5.00



PORCH FLOORING